

**Report 371980**

**Page 1 of 3**

Monteiro, Ribas -Revestimentos SA  
Estrada Ext. da Circunvalacao, 9020  
4202-351 Porto  
Portugal

Contact: Patricia Caetano

---

DATE RECEIVED	:	23 FEBRUARY 2021
DATE TESTED	:	24 MARCH 2021
QUALITY REFERENCE	:	SI 1251/197IG
REPUTED FIBRE CONTENT	:	PVC-74% + CO-26%
COLOUR / DESIGN	:	BROWN
FABRIC DESCRIPTION	:	COATED
END USE	:	UPHOLSTERY

---

REQUEST: BSEN1021-1: 2014 (smouldering cigarette)  
BSEN1021-2: 2014 (match flame equivalent)

---

RESULT: The sample tested meets the flammability performance requirements of BS EN 1021-1:2014 and BS EN 1021-2:2014

---



**S. WISEMAN**  
**LABORATORY DIRECTOR**



**L. SMITH**  
**FLAMMABILITY TECHNICIAN**

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



**1695**

**BS EN 1021-1/2:2014 Furniture - Assessment of the ignitability of upholstered furniture –  
Part 1 Ignition Source: Smouldering cigarette.  
Part 2 Ignition Source: Match flame equivalent.**

### **Conditioning**

Immediately prior to testing the sample ‘SI 1251/197IG’ was subjected to 24 hours in specified conditions, having a temperature of (23± 2°C) and relative humidity of (50±5%).

### **Procedure**

The specimens were mounted over fillings of combustion modified high resilience foam with a density of approximately 35-36 Kg/m<sup>3</sup>.

### **Results**

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

<u>Ignition Source</u>	<u>Ignitability Performance</u>
0	NI (Non-ignition)
0	NI (Non-ignition)
0	NI (Non-ignition)
1	NI (Non-ignition)
1	NI (Non-ignition)
1	NI (Non-ignition)

	Cigarette			Match-equivalent flame		
	1	2	3	1	2	3
<u>Smouldering Criteria</u> (Yes/No)						
Unsafe escalating combustion	No	No	/	No	No	No
Test assembly consumed	No	No	/	No	No	No
Smoulders to extremities	No	No	/	No	No	No
Smoulders through thickness	No	No	/	No	No	No
Smoulders more than 1 hour	No	No	/	No	No	No
More than 100mm from source	No	No	/	No	No	No
<u>Flaming Criteria</u> (Yes/No)						
Duration of flames (s)	N/A	N/A	/	1	1	1
Unsafe escalating combustion	No	No	/	No	No	No
Test assembly consumed	No	No	/	No	No	No
Flames to extremities	No	No	/	No	No	No
Flames through thickness	No	No	/	No	No	No

**Comments**

The sample tested meets the flammability performance requirements of BS EN 1021-1:2014 and BS EN 1021-2:2014

**Decision rules**

The decision rule applicable to statements of conformity relating to the test(s) carried out is simple acceptance based on the measured test results not falling within a range either side of a specified limit that is equal to the uncertainty of measurement for the parameter measured (based on 95% confidence levels). In all other regards, the decision rule is based on simple acceptance predicated upon the conditions of testing falling within the criteria for test set out in the test method with a conformance probability of 95%. The risk of false accept or false reject is therefore not greater than 2.5%.

Uncertainty of measurement: Timings ±0.4s  
Dimensions ±0.5mm

