

Our Ref: SW/BR

13 November 2020

Report 368136

Page 1 of 3

Oniro Textiles
Fahrenheitbaan 4B
3439 MD Nieuwegein
Netherlands

DATE RECEIVED	:	03 NOVEMBER 2020
QUALITY/REFERENCE	:	NIROXX LAMÉ
ONIRO REFERENCE	:	LAMÉ
REPUTED FIBRE CONTENT	:	100% PES
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	68007
BATCH NUMBER	:	420609_12199-1

REQUEST: *Flammability in accordance with IMO 2010 FTP Code annex 1 Part 8

COMMENTS: See results below



S. WISEMAN
LABORATORY DIRECTOR

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

*These tests have been sub-contracted

Our Ref: SW/BR

13 November 2020

Report 368136

Page 2 of 3

Testing to IMO FTP Code 2010: Part 8- Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C Temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 17°C.

Procedure

The samples were tested In accordance with IMO FTP Code 2010: Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m³.

Requirements

Ignition source 0 No progressive smouldering of flaming within 1 hour of the placement of the cigarette.

Ignition source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm) 68mm x 8mm
 Mass (g) 0.92
 Smouldering rate (mins/sec) 11.13

Cigarette test- Source 0

Specimen no	1	2
Extinction time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Pass/Fail	Pass	Pass

Result of cigarette test: Pass

Our Ref: SW/BR

13 November 2020

Report 368136

Page 3 of 3

Propane flame test- Source 1

Specimen no	1	2
Time if ignition (s)	5	6
Extinction time of flames after removal of burner (s)	2	1
Time of cover split (s)	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Pass/Fail	Pass	Pass

Result of the Flame test: Pass

In the opinion of the test house who carried out the testing, based on the test carried out on the sample supplied; the results indicate that the sample does meet the requirements according to IMO FTP code 2010, part 8.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.